

Lexan* 8A35 Film

Product Datasheet

Description

Lexan 8A35 is a one side velvet, one side polished transparent polycarbonate film. It offers high temperature resistance, excellent dimensional stability, as well as good printability without pre- treatment making it very suitable for multi-layer printing for applications such as overlays, floor graphics, high-performance labels and in-mould decoration. It can be screen printed using traditional solvent based or water based inks, as well as UV or infrared drying inks and offers ease of processing for thermoforming, embossing, die-cutting, hydro-forming and bending. The velvet texture offers mar resistance, and can be used over light-emitting devices (LEDs).

Typical Property Values ♦

| Property | ASTM Test Method | Units (USCS) | Value | ISO Test Method | Units (SI) | Value |
|---|-----------------------|-------------------------------|-----------------|-----------------|-------------------------|-----------|
| Mechanical | | | | | | |
| Tensile Strength @ Yield | ASTM D882 | psi | 8500 | ISO 527 | MPa | 62 |
| Ultimate | ASTM D882 | psi | 9000 | ISO 527 | MPa | 65 |
| Tensile Modulus | ASTM D882 | psi | 300000 | ISO 527 | MPa | 2506 |
| Tensile Elongation at Break | ASTM D882 | % | 100-160 | ISO 527 | % | 100-154 |
| Gardner Impact Strength at 0.03" (0.75 mm) | ASTM D3029 | ft-lb | 23 | ISO 6603-1 | J | 31 |
| Tear Strength | | | | | | |
| Initiation | ASTM D1004 | lb/mil | 1.4-1.8 | | kN/m | 245 |
| Propogation | ASTM D1922 | g/mil | 30-55 | | kN/m | 10-20 |
| Puncture Resistance (Dynatup) | ASTM D3763 | ft-lb | 9 | | J | 12 |
| Fold Endurance (MIT) | | | | | | |
| 0.010" (0.25 mm) | ASTM D2176-69 | double folds | 130 | | | |
| 0.020" (0.50 mm) | ASTM D2176-69 | double folds | 35 | | | |
| Thermal | | | | | | |
| Coefficient of Thermal Conductivity | ASTM D5470 | Btu/hr/ft ² /°F/in | 1.35 | | W/m ² K | 0.2 |
| Coefficient of Thermal Expansion | ASTM E831 | (x10 ⁻⁵ /°F) | 3.2 | ISO 11359 | (x10 ⁻⁵ /°C) | 5.8 |
| Specific Heat @40°F (4°C) | ASTM E1269 | Btu/lb/°F | 0.3 | | KJ/Kg-°C | 1.25 |
| Glass Transition Temperature | ASTM D3417 / D3418 | °F | 307 | ISO 11357 | °C | 153 |
| Vicat Softening Temperature, B | ASTM 1525-00 modified | °F | 323 | | °C | 160 |
| Heat Deflection Temp. by TMA at 1.8 Mpa | | °F | 290 | ISO 75 Modified | °C | 145 |
| Shrinkage at 302°F (150°C) | ASTM D1204 | % | 1.40 | | % | 1.40 |
| Brittleness Temperature | ASTM D746 | °F | -211 | | °C | -135 |
| Physical | | | | | | |
| Density | ASTM D792 | slug/ft ³ | 2.3 | ISO 1183 | kg/m ³ | 1200 |
| Water Absorption, 24 hrs. | ASTM D570 | % change | 0.35 | ISO 62 | % change | 0.35 |
| Surface Roughness (RMS) | ASME B46-1 | μ | 55 | | | |
| Surface Energy(1 st surface/ 2 nd surface) | ASTM D5946-01 | - | 34/34 | | | |
| Surface Tension(1 st surface/ 2 nd surface) | Dyne Pens | Dyne | 40-42/ 38-40 | | | |
| Optical | | | | | | |
| Refractive Index @77°F (25°C) | ASTM D542A | - | 1.6 | | | |
| Light Transmission | ASTM D1003 | % | 90 | | | |
| Yellowness Index | ASTM D1925 | % | 0.9 | | | |
| Haze | ASTM D1003 | % | 42 | | | |
| Gloss over Flat Black min/max @ 60° | ASTM D523-60 | - | see chart | ISO 2813 | - | see chart |

Manufacturing Specifications

| Nominal Gauge Ranges | Min./Max Limit of Nominal |
|--|------------------------------|
| 0.010-0.015" (0.250-0.375 mm) 0.020" (0.500 mm) | -/+5% -/+3% |
| Retardation (birefringence) | 300(nm) |


♦ These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local SABIC Innovative Plastics, Specialty Film & Sheet representative or the Quality Services Department. Reported values are based on 0.250 mm (0.010") thickness film unless otherwise noted.

* Trademark of SABIC Innovative Plastics IP BV

Lexan*

Gloss: (ASTMD 523-85)

| | Gauge | Angle | Velvet | |
|------|----------------------------------|-------|---------|----|
| 8A35 | 0.008 - 0.020" (0.200 - 0.500mm) | 85° | Minimum | 8 |
| | | | Maximum | 19 |



* Trademark of SABIC Innovative Plastics IP BV

Americas:
SABIC Innovative Plastics
Specialty Film & Sheet
One Plastics Avenue
Pittsfield, MA 01201
USA
Tel. (1) (413) 448 7110
Fax. (1) (413) 448 5573

Europe:
SABIC Innovative Plastics
Specialty Film & Sheet
Plasticslaan 1
NL - 4612 PX Bergen op Zoom
The Netherlands
Tel. (31) (164) 292911
Fax. (31) (164) 292940

Pacific:
SABIC Innovative Plastics
Specialty Film & Sheet
1468 Nanjin Road (W)
26th Floor, United Plaza
200040 Shanghai, China
Tel. (86) 21 3222 4500
Fax. (86) 21 6289 8998

THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BV, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT <http://www.sabic-ip.com> AND ARE AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION OR RECOMMENDATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SELLER'S PRODUCTS, SERVICES OR RECOMMENDATIONS. EXCEPT AS PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. No statement by Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC Innovative Plastics is a trademark of Sabic Holding Europe BV

* Trademark of SABIC Innovative Plastics IP BV